Thermal Conductivity

Material	Thermal conductivity (cal/sec)/(cm^2 C/cm)	Thermal conductivity (W/m K)*
Silver	1.01	406.0
Copper	0.99	385.0
Brass	...	109.0
Aluminum	0.50	205.0
Iron	0.163	...
Steel	...	50.2
Lead	0.083	34.7
Mercury	...	8.3
Ice	0.005	1.6
Glass,ordinary	0.0025	0.8
Concrete	0.002	0.8
Water at 20 C	0.0014	...
Asbestos	0.0004	...
Hydrogen at 0 C	0.0004	0.14
Helium at 0 C	0.0003	0.14
Oxygen	...	0.023
Snow (dry)	0.00026	...
Fiberglass	0.00015	0.04
Brick,insulating	...	0.15
Brick, red	...	0.6
Cork board	0.00011	0.04
Wool felt	0.0001	0.04
Rock wool	...	0.04
Styrofoam	...	0.01
Wood	0.0001	0.12-0.04
Air at 0 C	0.000057	0.024

*From Young, Hugh D., University Physics, 7th Ed. Table 15-5.

Heat conduction discussion

Debye Temperature and Thermal Conductivity

Index

Tables

Reference
Young
Ch 15.

HyperPhysics***** Thermodynamics

Go Back

Wiedemann-Franz Ratio

The ratio between thermal and electrical conductivities of metals can be expressed in terms of the ratio:

$$L = \frac{\kappa}{\sigma T} = \frac{\pi^2 k^2}{3e^2} = 2.45 \times 10^{-8} W\Omega / K^2$$

which may be called the Wiedemann-Franz Ratio or the Lorenz constant.

Metal	$\kappa/\sigma T$ ($10^{-8} W\Omega/K^2$)
Cu	2.23
Ag	2.31
Au	2.35
Zn	2.31
Cd	2.42
Sn	2.52
Mo	2.61
Pb	2.47
Pt	2.51

Heat conduction discussion

Wiedemann-Franz Law

Index

Tables

Reference
Blatt
Section
13.2

HyperPhysics***** Thermodynamics

Go Back

WOLFRAMRESEARCH   scienceworld.wolfram.com

ASTRONOMY   BIOGRAPHY   CHEMISTRY   MATHEMATICS   PHYSICS

Search Site

ERIC WEISSTEIN'S
WORLD OF **PHYSICS**

WORLD OF PHYSICS
- Astrophysics
- Electromagnetism
- Experimental Physics
- Fluid Mechanics
- History and Terminology
- Mechanics
- Modern Physics
- Optics
- States of Matter
- Thermodynamics
- Units & Dimensional Analysis
- Wave Motion

ALPHABETICAL INDEX

- **ABOUT THIS SITE**
- **FAQs**
- **WHAT'S NEW**
- **RANDOM ENTRY**
- **BE A CONTRIBUTOR**
- **SIGN THE GUESTBOOK**
- **EMAIL COMMENTS**

ERIC'S OTHER SITES

T

Thermal Conductivity

Thermal conductivity is defined by

$$k \equiv \rho c_P \kappa,$$

where c_P is the heat capacity and κ is the thermal diffusivity. In cgs, thermal conductivity is measured in erg cm^{-1} K^{-1} s^{-1}. For air (in MKS),

$$k_{air} = 0.03 \ \text{W} \ \text{m}^{-1} \ \text{K}^{-1}.$$

SEE ALSO: Electrical Conductivity, Thermal Diffusivity

Eric W. Weisstein

Related Wolfram Research Products Include:

✦ *Mathematica*   ∞ *CalculationCenter*